



TECHNICAL DATA SHEET

DESCRIPTION

BOREAL NATURE is a TYPE 2, medium density, spray applied polyurethane foam insulation system. This product is free of ozone depletion substances (Zero ODS). BOREAL NATURE is manufactured with renewable substances, recycled products and is blown with lavender water. BOREAL NATURE is lime green in colour.

BOREAL NATURE has been tested by an independent laboratory and accredited by the CCMC. It surpasses the CAN/ULC s705.1 requirements including amendments 1, 2 and 3 (*Standard for Thermal Insulation-Spray Applied Rigid Polyurethane Foam, medium Density, Material Specification standard*).

BOREAL NATURE must be applied by CUFCA licensed installers under the application standard CAN/ULC s705.2.

BOREAL NATURE is a Type Two insulation product – CCMC#14025-L.

TYPICAL PHYSICAL PROPERTIES

PHYSICAL PROPERTIES	STANDARD	RESULT
Core Density	ASTM D1622	33.6 kg/m ³ (2.09 lb/ft ³)
Compressive Strength	ASTM D1621	201 kPa (29.2 psi)
Tensile Strength	ASTM D1623	217 kPa (31.5 psi)
Water Vapour Permeance	ASTM E96 (core, 50mm)	45 ng/(Pa*s*m ²)
Surface burning (flame spread index)	CAN/ULC S102 (S127)	375
Smoke Develop Index	CAN/ULC S102	300
Initial Thermal Resistance	ASTM C518 (50 mm)	2.55 k*m ² /W (R 7.35 / inch)
Long Term Thermal Resistance (50mm)	CAN/ULC S770	2.03 k*m ² /W Type Two (R 6 / inch)
Air Permeance @ 75 Pa	CCMC 07273	0.0006 L/s.m ²
Volatile Organic Emissions – Recommended time to occupancy	CAN/ULC S774	24 hours
Open Cell Content	ASTM D2856	1.23%
Water Absorption	ASTM D2842 (by volume)	1.74%
Dimensional Stability	ASTM D2126 (28 days) -20°C, Ambient R.H.) 80°C, ambient R.H. 70°C, 97%RH (+-3% R.H.)	-0.60% 3.70% 4.10%

LONG-TERM THERMAL RESISTANCE

Thickness Mm (inches)	R-VALUE (ft ² *hr*°F/BTU)	RSI (m ² *K/W)
50.8 (2.00)	11.8	2.06
63.5 (2.50)	14.9	2.62
76.2 (3.00)	18.1	3.19
88.9 (3.50)	21.5	3.79
102.0 (4.00)	24.6	4.33
127.0 (5.00)	31.1	5.48
152.0 (6.00)	37.1	6.53
177.8 (7.00)	43.4	7.64
203.2 (8.00)	49.9	8.79

ADDITIONAL INFORMATION

- ✓ Maximum per pass thickness is 51mm (2 inches). Spraying thicker can result in spontaneous combustion and poor overall spray foam quality.
- ✓ Internal temperature of installed pass must be 25°C before installing subsequent passes. Maximum thickness during 24 hour period is 203mm (8 inches).
- ✓ Like all spray foam products, Genyk “Boreal” is combustible. An approved thermal barrier must be installed in accordance with applicable building codes.
- ✓ The service temperature of Genyk “Boreal” is between -60°C and 80°C.
- ✓ Recommended storage temperature of materials is from 10 to 25°C (50 to 77°F).

INSTALLATION GUIDELINES

BOREAL NATURE	Ambient Temperatures	Spraying Temperatures	Minimum Spray pressures
SUMMER	10 to 35°C (50 to 95°F)	35 to 41°C (95 to 105°F)	5516 kPa (800 psi)
INTERMEDIATE	0 to 15°C (32 to 59°F)	35 to 45°C (95 to 113°F)	5516 kPa (800 psi)
WINTER	-10 to 5°C (14 to 41°F)	38 to 50°C (100 to 122°F)	5516 kPa (800 psi)

COMPONENT PRODUCT SPECIFICATIONS

PROPERTY	POLYMERIC ISOCYANATE A-2732	BOREAL NATURE RESIN
COLOUR	Brown liquid	Dark liquid
Viscosity at 25°C	150-250 cps	200-400 cps
Specific gravity	1.22 – 1.25	1.17 – 1.21
Shelf life	12 months	6 months

REACTIVITY PROFILE

CREAM TIME	GEL TIME	RISE TIME
0 to 1 second	2 to 3 seconds	4 to 5 seconds

The information contained herein is based on information available to Genyk Inc. The data is considered an accurate description of the product performance and is presented in good faith. However, Genyk Inc. disclaims any liability for incidental or consequential damages which may result from the inappropriate use of this product. It is the user’s responsibility to thoroughly test the product in any application to determine performance, efficiency and safety. No information contained herein is to be considered as permission or recommendation to infringe on any patent or other intellectual property.